



RAVENOL Hochleistungsfett mit MoS2

RAVENOL Hochleistungsfett mit MoS2 is a lithium saponified grease with antioxidants, corrosion inhibitors and wear protection agents. Dry running properties are achieved by the addition of about 3% molybdenum disulfide.

RAVENOL Hochleistungsfett mit MoS2 has a very low internal friction value, and is therefore easy pumpable.

The optimized formulation of RAVENOL Hochleistungsfett mit MoS2 is resistant to salt water and can also be used at sea.

Application Notes

RAVENOL Hochleistungsfett mit MoS2 is used for the lubrication of places which are hard to get at and are often forget in maintenance, and for the lubrication of oscillating machine parts.

RAVENOL Hochleistungsfett mit MoS2 is also recommended for chassis lubricating.

Quality Classifications

RAVENOL Hochleistungsfett mit MoS2 is tried and tested for aggregates specifying:

Specifications

DIN 51 502: KPF2K-30, ISO 6743 Part 9: ISO-L-XCCIB2

Characteristic

RAVENOL Hochleistungsfett mit MoS2 offers:

- Excellent shear stability
- Outstanding corrosion protection
- Very good mechanical and chemical stability
- Very good aging resistant
- Good pump output also at low temperatures

Characteristics	Unit	Data	Audit
Colour		black-grey	visual
Thickener		Lithium Complex Soap	-
Additives		MoS2	-
NLGI-Class		2	DIN 51 818
DIN-Product-Classification		KPF2K-30	DIN 51 502
ISO-Product-Classification		ISO-L-XCCIB2	ISO 6743 P.9
Working Temperature	°C	-30 / +120	DIN 51 825
Short Term up to	°C	130	-
Worked Penetration 60 strokes	mm/10 bei 25°C	265-295	ISO 2137
Corrosion (SKF Emcor dist. Water)	Corr. Degree	0-1	DIN 51 802
Dropping Point	°C	180	DIN ISO 2176
Copper Corrosion (24h/120°C)		1	DIN 51 811
Water Resistance (3h/90°C)	°C	1-90	DIN 51 807 P.1
VKA Pressure Carrying Capacity	N	2800 - 3000	DIN 51 350 T.4
Kinematic Viscosity (Base Oil)	mm ² /s bei 40°C	80	DIN 51562-1

All indicated data are approximate values and are subject to the commercial fluctuations.

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

23.03.2016

Ravensberger Schmierstoffvertrieb GmbH

Postfach 1163

33819 Werther

Tel.: 05203/9719-0

Fax.: 052039719-40 / 41